AODISI

FIRE TECHNOLOGY

产品资料与销售咨询

PRODUCT DOCUMENTATION & SALES CONTACT

GEAQUELLO ® E 824 - Technical Data Sheet-en

澳迪斯防火科技（廊坊）有限公司

Aodisi Fire Technology (Langfang) Co., Ltd.

销售及选型联系 / Sales & product enquiries

19931333348

492048031@qq.com

www.gmfireproof.com

以上为销售联系信息，不替代安全数据表中的应急联系电话。
原始技术内容及制造商、检测机构和证书签发信息见后续资料页。

Sales contact only; emergency contacts in safety data sheets remain applicable.
Original technical, manufacturer and certification details follow.

GEAQUELLO® E 824

Impregnation fluid

Description

Impregnation fluid GEAQUELLO® E 824 for GEAQUELLO® systems E 795 and E 950.
GEAQUELLO® E 824 is an aqueous solution of colloidal silicic acid.



Areas of Application

- Ships & offshore
- Rolling stock
- In the sealing system GEAQUELLO® E 950
- In the sealing system GEAQUELLO® CPS
- In the sealing system GEAQUELLO® E 795

Delivery and Packaging

GEAQUELLO® E 842		
Packaging	bottle	can
Size	à 1 kg	à 10 kg
Article number		
	4145152	4145286

GEAQUELLO® E 824

Technical Data

Application instructions
Used for the impregnation of retaining modules. A spray cap for the 1 kg bottles is available. Use gloves and eye protection while working. Cover the work place with paper or foil.

Product properties	reacts neutrally physiologically safe not subject to hazard identification requirements
Colour	blue
Viscosity	< 10 mPa·s
Density	approx. 1.1 g/cm³
pH value (10 % solution)	7.0–8.0
Conductivity (10 % solution)	450–600
Boiling point	approx. 100 °C
Melting point	approx. 0 °C
Storage	Protect from frost! Cool and dry storage. Shelf life of at least 24 months in sealed original packaging.
Safety instructions	Consult the safety data sheet for additional instructions.