AODISI

FIRE TECHNOLOGY

产品资料与销售咨询

PRODUCT DOCUMENTATION & SALES CONTACT

KERAFIX ® FXL 200 - Certificate / Approval ETA-17/0960-en

澳迪斯防火科技（廊坊）有限公司

Aodisi Fire Technology (Langfang) Co., Ltd.

销售及选型联系 / Sales & product enquiries

19931333348

492048031@qq.com

www.gmfireproof.com

以上为销售联系信息，不替代安全数据表中的应急联系电话。
原始技术内容及制造商、检测机构和证书签发信息见后续资料页。

Sales contact only; emergency contacts in safety data sheets remain applicable.
Original technical, manufacturer and certification details follow.

Deutsches Institut für Bautechnik

DIBt

Member of EOTA

www.eota.eu

Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and Laender Governments

Designated according to Article 29 of Regulation (EU) No 305/2011 and member of EOTA (European Organisation for Technical Assessment)

European Technical Assessment

ETA-17/0960 of 17 September 2018

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:	Deutsches Institut für Bautechnik
Trade name of the construction product	Kerafix® FXL 200
Product family to which the construction product belongs	Intumescent products for fire sealing and fire stopping purposes
Manufacturer	Rolf Kuhn GmbH Jägersgrund 10 57339 Erndtebrück DEUTSCHLAND
Manufacturing plant	1[1]
This European Technical Assessment contains	6 pages including 1 annex which forms an integral part of this assessment
This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of	EAD 350005-00-1104

[1] Address known at DIBt

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

Object of this European Technical Assessment (ETA) is the intumescent construction product "Kerafix® FXL 200" and the described modifications.

In case of fire, exposed to high temperatures, the intumescent product expands and generates foam. This foam seals joints and gaps, closes voids and openings. Thus, the foam restricts the passage and the spread of heat, smoke, flames or any combination of these.

During the reaction the product does not develop essential expansion pressure.

The flexible intumescent construction product "Kerafix® FXL 200" is produced in form of mats, strips and cuts. The product consists essentially of intumescent substances and a binder. It is produced of nominal thicknesses between 0,7 mm and 3,2 mm with a tolerance in thickness of ± 10 % for each and in any width between 5 mm and 340 mm. The product may be laminated, processed to blanked-out pieces, cuts or strips at the factory.

The construction product "Kerafix® FXL 200" and cuts of it may be laminated additionally on one side or completely wrapped with plastic foil.

This ETA covers the following modifications besides the non-laminated basic variant named "Kerafix® FXL 200":

- laminated with PVC-foil[2] of different colours on one side; named "Kerafix® FXL 200 DF",
- laminated with PE-sellotape[2] on one side, named "Kerafix® FXL 200 ZPE",
- laminated with textile tape[2] on one side, named "Kerafix® FXL 200 GW",
- laminated with glass fibre scrim[2] on one side, named "Kerafix® FXL 200 GG",
- laminated with glass non-woven[2] on one side, named "Kerafix® FXL 200 GV",
- laminated with aluminum-folie[2] on one side, named "Kerafix® FXL 200 AF" or
- completely wrapped with PVC- or acrylic foil[2], named "Kerafix® FXL 200 E".

The product and all its modifications may be additionally finished with a self-adhesive tape[2] on one side.

The construction product is delivered in rolls or factory made strips and cuts.

The technical characteristics relevant for fire sealing and fire stopping effects of the construction product "Kerafix® FXL 200" are given in Annex 1.

2 Specification of the intended use in accordance with the applicable European Assessment Document (EAD)

The construction product "Kerafix® FXL 200" is assessed on the basis of EAD 350005-00-1104[3] as an intumescent product for fire sealing and fire stopping purposes without defined final intended use (IU 1).

The construction product and its modifications are intended to be used as an essential component in construction products, construction elements, assemblies, kits and special constructions which need to meet requirements concerning the safety in case of fire.

In case of fire, the product delays the heat transfer through fire resistant construction products, construction elements or structures by expanding under the impact of high temperatures and thus restricting the spread of fire.

2 Type, manufacturer and characteristics deposited at DIBt.
3 Official Journal of the EU N° C 378/02 of 13/11/2015

The performance given in section 3 is only valid, if the construction product "Kerafix® FXL 200" in use considers the instructions and the conditions stated in section 3.3.

The test and assessment methods on which this European Technical Assessment is based, lead to the assumption of working life of the intumescent construction product "Kerafix® FXL 200" of at least 10 years[4] in final use.

The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for this assessment

3.1 Safety in case of fire (BWR 2)

3.1.1 Reaction to fire

Reaction to fire of product:	Performance
"Kerafix® FXL 200" without any lamination or self-adhesive devices and the modifications described in section 1: "Kerafix® FXL 200 DF", "Kerafix® FXL 200 ZPE", "Kerafix® FXL 200 GW", "Kerafix® FXL 200 GG", "Kerafix® FXL 200 GV", "Kerafix® FXL 200 AF" and "Kerafix® FXL 200 E"	Class E in accordance with EN 13501-1[5].

3.1.2 Resistance to fire

The performance "resistance to fire" shall be determined separately for every final use and shall be classified, if required for the construction element concerned.

3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content of dangerous substances	No dangerous substances[6]

The detailed chemical composition of the intumescent construction product "Kerafix® FXL 200" was assessed by DIBt and is deposited with DIBt.

3.3 General aspects

Durability testing shall be an integral part of assessing the basic works and performance requirements. The following specific provisions for use shall be complied with to ensure the durability of the performance.

The testing and the assessment of the relevant product performance were carried out for environmental conditions of type $Y_{2(-5°C/+70°C)}$ – product intended for use at temperatures between -5 °C and +70 °C without any exposureto UV-radiation; indoor use at changing humidity, temporary or permanent condensation - in accordance with EOTA Technical Report 24 (EOTA TR 024)[7], section 4.2.5

4 Results (historical data) of long-term aging (10 years exposure to natural weathering) available

5 EN 13501-1 Fire classification of construction products and building elements, Part 1 Classification using test data from reaction to fire tests and A1:2009

6 In accordance with the Regulation (EC) No 1272/2008 of the European Parliament and of the Council of 16 December 2008 (published in the Official Journal of the EU N° L 353 of 31/12/2008, p 1)

7 EOTA TR 024 Characterisation, Aspects of Durability and Factory Production Control for Reactive Materials, Components and products; edition as amended July 2009

Result:

The intumescent construction product "Kerafix® FXL 200" and its modifications and cuts can be used under use conditions of type $Y_{2(-5°C/+70°C)}$ (indoor use at the stated range of temperatures), without having to fear essential changes in the relevant fire sealing and fire stopping properties and the resulting performance.

This assessment includes the in-door use under climatic use conditions of type Z_1 and Z_2 according to EOTA TR 024[7].

Additionally the product was successfully tested under specific durability conditions according to EOTA TR 024, section 4.3

- Exposure to a constant temperature of 80 °C for 40 days,
- Exposure to solvents (tested with Butylacetat, Butanol, solvent naphtha and fuel)
- Subsequent over-painting (tested with coatings on the basis of acryl dispersion, alkyd resin, polyurethanacryl and epoxy resin),
- Exposure to intimate contact to plastics (PVC, PE).

The characteristics "expansion ratio" and "expansion pressure" did not change essentially after these exposures.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD No 350005-00-1104 the Decision of the commission N° 1999/454/EC of 22 June 1999 (OJ of the EU L 178 of 14 July 1999, p 42), amended by EC Decision 2001/596/EC of 8 January 2001 (OJ of the EU L 209 of 2 August 2001, p 33) is the legal basis for the determination of the AVCP system.

So system 1 applies for the assessment and verification of constancy of performance (AVCP). (See Annex V in conjunction with Article 65 (2) of the Regulation (EU) N° 305/2011) according to the following table:

Product	Intended use	characteristic	System
"Kerafix® FXL 200" and the modifications described in clause 1	Components effective in view of safety in case of fire (BWR 2) used in construction products, construction elements, kits and special assemblies	reaction to fire, properties relevant for the fire sealing and fire stopping effect	1

5 Technical details necessary for the implementation of the procedure for assessment and verification of constancy of performance (AVCP) system 1, as provided for in the applicable European Assessment Document

The technical details necessary for the implementation of the system for assessment and verification of constancy of performance are laid down in the control plan (confidential part of this ETA) deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 17. September2018 by Deutsches Institut für Bautechnik

Maja Tiemann
p. p. Head of Department

beglaubigt:
Dr.-Ing. Dierke

Deutsches Institut für Bautechnik DIBt

ANNEX 1

CHARACTERISTICS[2] OF[3] THE[4] CONSTRUCTION[5] PRODUCT[6] RELEVANT FOR THE FIRE SEALING AND FIRE STOPPING EFFECTS OF

"Kerafix® FXL 200"[7]

Characteristic	Test method[8]	Range of determined values and tolerances*
Nominal thickness	TR 024[7], Abs. 3.1.2	0,7 mm to 3,5 mm ± 10 % for each
Expansion ratio	TR 024[7], Abs. 3.1.11 Tested at 400 °C for 30 minutes without a top-load for samples of a thickness of 0,7 mm and of 3,5 mm	thickness 0,7 mm: 30,0 to 50,0 thickness 3,5 mm: 17,0 to 30,0

The reaction in case of fire starts at a temperature of ca 200 °C.

[8] Details of the test methods are deposited with DIBt